



DESCRIPTION

- a two component surface tolerant high solids, direct to metal high build polyamine adduct cured epoxy coating
- approved to APAS 2973
- conforms to AS/NZS 3750.14

PRINCIPAL CHARACTERISTICS

- maintenance coating for use in a wide range of industrial applications as a primer, build coat or finish coat
- tolerant to lower grades of steel preparation for atmospheric exposure
- excellent recoatability
- cures down to +5°C
- excellent abrasion resistance
- resistant to splash of alkali, mineral oils, solvents and dilute acids
- suitable for immersion in salt and fresh water

COLOURS AND GLOSS

- AS 2700 Colour card, micaceous iron oxide colour range - gloss

BASIC DATA AT 25°C

- solids content approx. 85% by volume
- mix ratio 3A:1B by volume
- recommended dry film thickness 150 - 400 microns(dry), 175 - 475 microns(wet)
- theoretical spreading rate 5.7 m²/litre for 150 microns; 2.1 m²/litre for 400 microns
- touch dry after 2 - 4 hours
- overcoating interval..... refer to overcoating table for details
- full cure 5 days
- shelf life (cool and dry place) at least 12 months

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- all surfaces to be coated must be clean, dry and free from chalking and contamination
- previous suitable coat; dry and free from any contamination and sufficiently roughened if necessary
- oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning
- mild steel; blast clean in accordance with AS 1627.4 to Sa 2½ minimum (AS 1627.9), surface profile 40-70 microns
- mild steel; power tool clean in accordance with AS 1627.2 to St 2 minimum (AS 1627.9), (atmospheric exposure only)
- if oxidation occurs between blasting and application, the surface should be reblasted to the specified visual standard
- surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner
- substrate temperature must be at least 5°C during application and 3°C above dew point
- relative humidity should not exceed 85%



INSTRUCTIONS FOR USE

- mixing ratio by volume: base to hardener 3A:1B
- mix with EpinameL DTM985 Part B only
- induction time - none
- pot life at 25°C - 2 hours
- stir the components and mixed product well using a mechanical mixer
- the temperature of the mixed product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in lower sag resistance and slower cure
- thinner should only be added after mixing the components
- freshly catalysed material should not be added to product that has been mixed for some time
- for recommendations outside those contained in this data sheet, refer to WattyL

APPLICATION

- **AIRLESS SPRAY**
 - recommended thinner L760
 - volume of thinner 0-5%
 - nozzle orifice..... approx. 0.53 - 0.58 mm (0.021 - 0.023 inch)
 - nozzle pressure 15 MPa (2100 psi)
- **AIR SPRAY**
 - recommended thinner L760
 - volume of thinner 0-10%
 - nozzle orifice..... 1.5-2mm
 - nozzle pressure 0.2-0.4 MPa (30-60 psi)
- **BRUSH/ROLLER (only for touch up and spot repair)**
 - recommended thinner L760
 - volume of thinner 0-10%
- **CLEANING SOLVENT** L760

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

**ADDITIONAL DATA****Overcoating table with Epiname DTM985**

Substrate Temperature	5°C	15°C	25°C	35°C
Minimum interval	16 hrs	6 hrs	3 hrs	2 hrs
Maximum interval	3 months	3 months	2 month	2 months

- surface must be dry and free from chalking and contamination

Overcoating table with two pack polyurethane coatings

Substrate Temperature	5°C	15°C	25°C	35°C
Minimum interval	16 hrs	8 hrs	4 hrs	2 hrs
Maximum interval	1 month	1 month	1 month	1 month

- surface must be dry and free from chalking and contamination

Overcoating table with Paracryl IFC540 and SeaPro TC170

Substrate Temperature	5°C	15°C	25°C	35°C
Minimum interval	16 hrs	8 hrs	4 hrs	2 hrs
Maximum interval	1 month	1 month	14 days	7 days

- surface must be dry and free from chalking and contamination

Curing Table

Paint temperature	Dry to handle	Full cure
5°C	24 hours	14 days
15°C	10 hours	7 days
25°C	5 hours	5 days
35°C	3 hours	3 days

- adequate ventilation must be continuously maintained during application and curing

Potlife (at application viscosity)

Paint temperature	Potlife
15°C	4 hrs
25°C	2 hrs
35°C	1 hr

For the most up to date information contact Wattyl Customer Service Hotline or visit the Wattyl Website.

CUSTOMER SERVICE HOTLINE
WEBSITE

Australia
132 101
<http://www.wattyl.com.au>

New Zealand
0800 735 551
<http://www.wattyl.co.nz>

Wattyl and Epiname are registered trademarks of Wattyl Australia Pty Ltd.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive. 3. For all product and non-product related information, Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office. 4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.
WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)